OUTRAGE

TECHNICAL SPECIFICATION

MODEL	OUTRAGE IS
SIZE	30X60
THICKNESS	9.5 MM.
TYPE OF PRODUCT	PORCELAIN TILE
NATURE OF SURFACE	GLAZED
GROUP	B I a
REF.STANDARD	GB/T 3810

TEST DESCRIPTION	STANDARD TEST METHOD	STANDARD REQUIREMENTS ISO 13006 / EN 14411	TRENDY TILES SPECIFICATION
Length & Width	GB/T 3810.2	_+0.5%	_+0.01%
Thickness	GB/T 3810.2	_+5%	_1.01%+0.25%
Straightness of Sides	GB/T 3810.2	_+0.3%	_+0.03%
Rectangularity	GB/T 3810.2	_+0.5%	_+0.1
Surface Flatness	GB/T 3810.2	_+0.4%	_+0.1
Surface Quality	GB/T 3810.2	95% free of v. defect	Pass
Water Absorption	GB/T 3810.3	_<0.5%	0.09%
Breaking Strenght	GB/T 3810.4	_>1300 N	1971N
Modulus of Rupture	GB/T 3810.4	minimum 35MPa	43.8MPa
Resistance to Surface Abrasion	GB/T 3810.4	Manufacturers to state	4
Resistance to Thermal Shock	GB/T 3810.9	test method available	Fully resistant
Crazing resistance	GB/T 3810.11	Required	Fully resistant
Frost Resistance	GB/T 3810.12	Required	Fully frost resistant
Resistance to Household Chemicals & swimming pool salt	GB/T 3810.13	Minimum Class GB	GA
Resistance to Low Concentrations acids & alkalis	GB/T 3810.13	Manufacturers to state	GLB
Resistance to Stains	GB/T 3810.14	Minimum Class 3	class 5