LASSA PO

TECHNICAL DATA

11190 NW 25th Street, Suite 100
MIAMI, FL 33172
www.rocatileusa.com

Format:	**All formats available**	Type:	**Glazed Polished Porcelain**
Color:	**All colors available**	Thickness:	**7.0 mm (24X48)** **8.5 mm (12X24)**
Graphic:	**8 (24X48)** **16 (12x24)**	Recycled Content:	**5% *Pre-Consumer**

	ASTM Test	ISO Test	Value Required ANSI	Declared ASTM
WATER ABSORPTION	C373	ISO.10545/3	≤0.5%	≤0.5%
BREAKING STRENGHT	C648	ISO.10545/4	≥ 350	≥350
SCRATCH HARDNESS	MOH's Scale	EN-101	-	3
CHEMICAL RESISTANCE	C650	ISO-10545/13	Unaffected	Unaffected
FROST RESISTANCE	C1026	ISO-10545/12	Resistant	Resistant
GROUP	SEE FAQS	SEE FAQS	-	4
PEI - GLAZED TILES	C1027	ISO-10545/7	-	III
MINIMUM BOND STRENGHT (PSI)	C482	-	≥50 psi	165
DYNAMIC COEFFICIENT OF FRICTION (DCOF)	A137.1	-	≥0.42	<0.40
SHADE AND TEXTURE RATING	CTDA "V"	-	-	V2
FACIAL DIMENSIONS	C499	ISO-10545/2	1.5% Max	Pass
RANGE OF THICKNESS	C499	ISO-10545/2	0.040 Max	Pass
WARPAGE	C485	ISO-10545/2	0.75%	Pass
WEDGING	C502	ISO-10545/2	1.0% Max	Pass

***Contains a percentage of pre-consumer recycled content superior to 25% which has been certified by Bureau Veritas.**

Signature:
Marketing and Product Department

MARKETING & PRODUCT DEPT
11190 NW 25th Street, Suite 100
MIAMI, FL 33172
www.rocatileusa.com

Release Date
09/25/2023

LASSA PO

TECHNICAL DATA

11190 NW 25th Street, Suite 100
MIAMI, FL 33172
www.rocatileusa.com

Format:	**All formats available**	Type:	**Glazed Porcelain**
Color:	**All colors available**	Thickness:	**7.0 mm (24X48)** **8.5 mm (12X24)**
Graphic:	**8 (24X48)** **16 (12x24)**	Recycled Content:	**5% *Pre-Consumer**

	ASTM Test	ISO Test	Value Required ANSI	Declared ASTM
WATER ABSORPTION	C373	ISO.10545/3	≤0.5%	≤0.5%
BREAKING STRENGHT	C648	ISO.10545/4	≥ 350	≥350
SCRATCH HARDNESS	MOH's Scale	EN-101	-	5
CHEMICAL RESISTANCE	C650	ISO-10545/13	Unaffected	Unaffected
FROST RESISTANCE	C1026	ISO-10545/12	Resistant	Resistant
GROUP	SEE FAQS	SEE FAQS	-	4
PEI - GLAZED TILES	C1027	ISO-10545/7	-	IV
MINIMUM BOND STRENGHT (PSI)	C482	-	≥50 psi	165
DYNAMIC COEFFICIENT OF FRICTION (DCOF)	A137.1	-	≥0.42	≥0.42
SHADE AND TEXTURE RATING	CTDA "V"	-	-	V2
FACIAL DIMENSIONS	C499	ISO-10545/2	1.5% Max	Pass
RANGE OF THICKNESS	C499	ISO-10545/2	0.040 Max	Pass
WARPAGE	C485	ISO-10545/2	0.75%	Pass
WEDGING	C502	ISO-10545/2	1.0% Max	Pass

***Contains a percentage of pre-consumer recycled content superior to 25% which has been certified by Bureau Veritas.**

Signature:
Marketing and Product Department

MARKETING & PRODUCT DEPT
11190 NW 25th Street, Suite 100
MIAMI, FL 33172
www.rocatileusa.com

Release Date
09/25/2023